

Technical Data Sheet

Typical Application — General Purpose , HVAC

Premi-Glas® 1200H-10 is a fiberglass reinforced thermoset sheet molding compound for general purpose applications requiring thermal stability and stiffness.

**Key Features and Benefits:**

- Good dimensional stability, including excellent thermal resistance.
- Pigmentable for molded-in color; best appearance with mold texture.
- Excellent property retention in cold and hot environments.
- Suitable for outdoor use in applications involving UV exposure and water immersion in accordance with UL746C (f1), see File E42524

Typical Values. Mechanical values are for Specimens cut from Compression-Molded panels.			
Properties	Test Method	Values (US)	Values (Metric)
Tensile Strength	ASTM D-638	3,000 psi	20 MPa
Tensile Modulus	ASTM D-638	1.6 x 10 <sup>6</sup> psi	11 GPa
Flexural Strength	ASTM D-790	10,000 psi	70 MPa
Flexural Modulus	ASTM D-790	1.4 x 10 <sup>6</sup> psi	9.5 GPa
Notched Izod	ASTM D 256	5.8 ft*lb/in	310 Joules/m
Unnotched Impact	ASTM D 4812	6.8 ft*lb/in	365 Joules/m
Compressive strength	ASTM D-695	17,500 psi	120 MPa
UL Relative Thermal Index (electrical)	UL 746C	266 deg F	130 deg C
UL Relative Thermal Index (mechanical)	UL 746C	266 deg F	130 deg C
UL Relative Thermal Index (impact)	UL 746C	266 deg F	130 deg C
Flame Resistance	U.L. 94 HB	Pass, 0.060 in	Pass, 1.5 mm
Dielectric Strength, KV/mm	ASTM D149	380 Volts/mil	15 kV/mm
Arc resistance, seconds	ASTM D495	180 sec	180 sec

This SMC product is generally intended to be compression molded in matched metal die molds, typically at 300°F (150°C) and 500 to 1000 psi (35-65 BAR) molding pressure. Strength values may be affected by the molding process. Nominal values for polymerization shrinkage (0.002 to 0.0035 in/in) and specific gravity (1.70 to 1.85) may be customized for individual applications. Contact your Premix sales representative for specific design recommendations.

**Following physical characteristics are typical of this product:**

CLTE, XY direction: 25 ppm/ deg C
CLTE, Z direction: 35 ppm/deg C
Thermal Conductivity: 0.3 W/m <sup>2</sup> deg K
Poisson's Ratio: 0.3

**The values presented in this data sheet are typical values and are not to be interpreted as product specifications.**

All statements, information and data given herein are believed to be accurate and reliable but are presented without guarantee, expressed or implied.

*Last modified: 7/29/2009*