

Technical Data Sheet

Typical Application — Construction/General Purpose

Premi-Glas® 1205 is a fiberglass reinforced thermoset sheet molding compound for residential entry door skins and other general purpose applications.

Key Features and Benefits:

- Good warp resistance and dimensional repeatability.
- Good flow and fill in thin moldings.
- Excellent resistance to sagging and distortion during door assembly.
- Outstanding appearance in wood-grain texture or smooth skin applications.
- Standard colors are beige and white.

Typical Values. Mechanical values are for Specimens cut from Compression-Molded panels.			
Properties	Test Method	Values (US)	Values (Metric)
Flexural Strength	ASTM D-790	16,000 psi	110 MPa
Flexural Modulus	ASTM D-790	1.5 x 10 ⁶ psi	10 GPa
Tensile Strength	ASTM D-638	6,000 psi	40 MPa
Tensile Modulus	ASTM D-638	1.5 x 10 ⁶ psi	10 GPa
Tensile Elongation	ASTM D-638	0.8%	0.8%
Notched Izod	ASTM D 256	10 ft*lb/in	550 Joules/m
Unnotched Impact	ASTM D 4812	12 ft*lb/in	650 Joules/m

This SMC product is generally intended to be compression molded in matched metal die molds, typically at 300°F (150°C) and 500 to 1000 psi (35-65 BAR) molding pressure. Strength values may be affected by the molding process. Nominal values for polymerization shrinkage (0.0004 in/in) and specific gravity (1.80) may be customized for individual applications. Contact your Premix sales representative for specific design recommendations.

Following physical characteristics are typical of this product:

CLTE, XY direction: 25 ppm/ deg C
CLTE, Z direction: 35 ppm/deg C
Thermal Conductivity: 0.3 W/m*deg K
Poisson's Ratio: 0.3

The values presented in this data sheet are typical values and are not to be interpreted as product specifications.
All statements, information and data given herein are believed to be accurate and reliable but are presented without guarantee, expressed or implied.

Last modified: 7/29/2009