

Technical Data Sheet

Typical Application — Mass Transit

Premi-Glas® 3404 is a fiberglass reinforced thermoset sheet molding compound for mass transit and semi-structural applications where low smoke and low flammability are required.

Key Features and Benefits:

- Radiant panel flame spread index of less than 35 per ASTM E-162.
- Smoke Density of less than 25 per ASTM E662 (NBS smoke chamber).
- Accepts powder in-mold-coatings.
- Excellent flexural strength and outstanding toughness.
- Halogen-free flame retardant system for reduced smoke toxicity.

Typical Values. Mechanical values are for Specimens cut from Compression-Molded panels.			
Properties	Test Method	Values (US)	Values (Metric)
Flexural Strength	ASTM D-790	27,500 psi	190 MPa
Flexural Modulus	ASTM D-790	1.5 x 10 ⁶ psi	10 GPa
Tensile Strength	ASTM D-638	13,000 psi	90 MPa
Tensile Modulus	ASTM D-638	1.5 x 10 ⁶ psi	10 GPa
Tensile Elongation	ASTM D-638	1.2%	1.2%
Notched Izod	ASTM D 256	10 ft*lb/in	550 Joules/m
Unnotched Impact	ASTM D 4812	18 ft*lb/in	950 Joules/m
Radiant Panel Flame Index	ASTM E-162	35 or less	35 or less
NBS Smoke Density Index, Ds @ 4 minutes.	ASTM E-662	25 or less	25 or less

This SMC product is generally intended to be compression molded in matched metal die molds, typically at 300°F (150°C) and 500 to 1000 psi (35-65 BAR) molding pressure. Strength values may be affected by the molding process. Nominal values for polymerization shrinkage (0.0003 in/in) and specific gravity (1.83) may be customized for individual applications. Contact your Premix sales representative for specific design recommendations.

Following physical characteristics are typical of this product:

CLTE, XY direction: 25 ppm/ deg C
CLTE, Z direction: 35 ppm/deg C
Thermal Conductivity: 0.3 W/m²deg K
Poisson's Ratio: 0.3

The values presented in this data sheet are typical values and are not to be interpreted as product specifications.
All statements, information and data given herein are believed to be accurate and reliable but are presented without guarantee, expressed or implied.

Last modified: 7/29/2009