

Technical Data Sheet

Typical Applications — Automotive Body Panel/Personal Water Craft/Structural

Premi-Glas® 1203-30 is a versatile fiberglass reinforced thermoset sheet molding compound for automotive body panel, personal watercraft or structural and semi-structural applications where excellent surface appearance, high strength, and durability are required.

Key Features and Benefits:

- Excellent surface profile for highly visible painted surfaces.
- Low moisture absorption and long term durability.
- Accepts automotive primers and powder in-mold-coatings.
- Excellent flexural strength and outstanding toughness.
- Standard colors are unpigmented or grey. Limited pigmentability.

Typical Values. Mechanical values are for Specimens cut from Compression-Molded panels.			
Properties	Test Method	Values (US)	Values (Metric)
Flexural Strength	ASTM D-790	30,500 psi	210 MPa
Flexural Modulus	ASTM D-790	1.5 x 10 ⁶ psi	10 GPa
Tensile Strength	ASTM D-638	14,500 psi	100 MPa
Tensile Modulus	ASTM D-638	2.2 x 10 ⁶ psi	15 GPa
Tensile Elongation	ASTM D-638	1.2%	1.2%
Notched Izod	ASTM D 256	18 ft*lb/in	950 Joules/m
Unnotched Impact	ASTM D 4812	28 ft*lb/in	1500 Joules/m

This SMC product is generally intended to be compression molded in matched metal die molds, typically at 300°F (150°C) and 500 to 1000 psi (35-65 BAR) molding pressure. Strength values may be affected by the molding process. Nominal values for polymerization shrinkage (0.00025 in/in expansion) and specific gravity (1.95) may be customized for individual applications. Contact your Premix sales representative for specific design recommendations.

Following physical characteristics are typical of this product:

CLTE, XY direction: 25 ppm/ deg C
CLTE, Z direction: 35 ppm/deg C
Thermal Conductivity: 0.3 W/m*deg K
Poisson's Ratio: 0.3

The values presented in this data sheet are typical values and are not to be interpreted as product specifications.
All statements, information and data given herein are believed to be accurate and reliable but are presented without guarantee, expressed or implied.

Last modified: 5/12/2010