

Technical Data Sheet

Typical Application — Composite Powertrain/Structural

Premi-Glas® 1286 is a fiberglass reinforced thermoset sheet molding compound employing hybrid vinyl ester/polyester resin technology for automotive powertrain and other structural or semi-structural applications.

Key Features and Benefits:

- Excellent thermal properties and elevated temperature modulus retention.
- Replaces cast metals for reduced Noise, Vibration, and Harshness.
- Excellent resistance to automotive chemicals and salt spray.
- Meets the requirements of GMP.UP.018 and other specs.
- Designed for compression molding of large-span valve covers.

Typical Values. Mechanical values are for Specimens cut from Compression-Molded panels.			
Properties	Test Method	Values (US)	Values (Metric)
Flexural Strength, RT	ISO 178	29,000 psi	200 MPa
Flexural Modulus, RT	ISO 178	1.9 x 10 ⁶ psi	13 GPa
Flex Strength, 150 deg C	ISO 178	16,000 psi	108 MPa
Flex Modulus, 150 deg C	ISO 178	1.2 x 10 ⁶ psi	8 GPa
Tensile Strength, RT	ISO 527	12,000 psi	80 MPa
Tensile Modulus, RT	ISO 527	2.0 x 10 ⁶ psi	14 GPa
Tensile Strength, 150 deg C	ISO 527	9,300 psi	64 MPa
Tensile Modulus, 150 deg C	ISO 527	1.35 x 10 ⁶ psi	9.3 GPa
Unnotched Impact	ASTM D 4812	25 ft*lb/in	1350 Joules/m
Water Absorption	ISO 62	0.1%	0.1%
Glass Transition Temperature (Tg)	ISO 6721 DMS	410 deg F	210 deg C
High Speed Impact, deflection at max load	ISO 6603-2	0.19 in	4.9 mm
High Speed Impact, impact at max load	ISO 6603-2	740 lbs	3.3 KN
High Speed Impact, energy at max load	ISO 6603-2	5.8 ft*lb	7.8 Joules
High Speed Impact, total energy	ISO 6603-2	13.9 ft*lb	18.8 Joules

This SMC product is generally intended to be compression molded in matched metal die molds, typically at 300°F (150°C) and 500 to 1000 psi (35-65 BAR) molding pressure. Strength values may be affected by the molding process. Nominal values for polymerization shrinkage (0.001 in/in) and specific gravity (1.82) may be customized for individual applications. Contact your Premix sales representative for specific design recommendations.

Following physical characteristics are typical of this product:

CLTE, XY direction: 20 ppm/ deg C
CLTE, Z direction: 35 ppm/deg C
Thermal Conductivity: 0.45 W/m*deg K
Poisson's Ratio: 0.3

The values presented in this data sheet are typical values and are not to be interpreted as product specifications.
All statements, information and data given herein are believed to be accurate and reliable but are presented without guarantee, expressed or implied.

Last modified: 7/29/2009